



Lead-Free Solder Paste

PF606-P30

Rev. 2016/03/01 Ver. 02-01

BASIC OVERVIEW



SnAg3.0Cu0.5X Solder Paste
Halide Free
No Clean
Low Voiding

APPLICATIONS

Universal Lead-Free SMD Solder Paste
Wide Range of Applications and PCB designs

FEATURES

Appearance	Gray paste w/o visible foreign and clusters	
Alloy Composition	Sn/Ag3.0/Cu0.5/x	JIS-Z-3282
Melting Point	217~219 °C	
Particle Size	(Type 3) +45μm < 1% , - 20μm < 10% (Type 4) +38μm < 1% , - 20μm < 10% (Type 5) +25μm < 1% , - 15μm < 10% (Type 6) +15μm < 1% , - 5μm < 10%	IPC-TM-650, 2.2.14
Powder Shape	Spherical	
Flux Content	11.5 ± 1.0 wt%	JIS-Z-3197, 8.1.2
Halide Content	< 0.0 wt% (in flux)	J-STD-004
Viscosity	200 ± 30 Pa.s (25±1°C, 10rpm, Malcom)	JIS-Z-3284 Annex 6
Flux Type	ROLO	J-STD-004

Alloy Detail Composition

(Sn)	(Ag)	(Cu)	(Ni)	(Ge)	(Zn)	(Al)	(Sb)	(Fe)	(As)	(Bi)	(Cd)	(Au)	(In)	(Pb)
REM.	2.8~ 3.2	0.3~ 0.7	0~ 0.01	0~ 0.01	0.001 MAX	0.001 MAX	0.05 MAX	0.02 MAX	0.03 MAX	0.10 MAX	0.002 MAX	0.05 MAX	0.10 MAX	0.05 MAX

Patent No.: Japanese Patent No. 3296289, U.S Patent No. 6179935B1, Germany Patent No.19816671C2

(wt%)

Scan Code for Solder
Paste Documents





Lead-Free Solder Paste

PF606-P30

Rev. 2016/03/01 Ver. 02-01


PERFORMANCE & RELIABILITY

Copper Plate Corrosion Test	Pass	JIS-Z-3197, 8.4.1
Spreading Test	> 70%	JIS-Z-3197, 8.3.1.1
Ion Chromatography Test	0.0 wt%	IPC-TM-650 Method 2.3.28.1
Copper Mirror Test	Pass	IPC-TM-650, 2.3.32
Viscosity Test (25°C,10 rpm)	200 ± 30 Pa.s	JIS-Z-3284. Annex 6
Tackiness Test (gf)	> 130 (8hr)	JIS-Z-3284. Annex 9
Slump Test	Pass	JIS-Z-3284. Annex 7,8
Solder Ball Test	Pass	JIS-Z-3284. Annex 11

S.I.R. Test ▲	> 1×10 ⁹ Ω, Pass	IPC-TM-650, 2.6.3.3
Electro Migration Test ◆	Pass	IPC-TM-650, 2.6.14.1

▲ Test Conditions : 85 °C, 85% RH for 168 hrs ◆ Test Conditions : 65 °C, 88.5% RH for 596 hrs

RECOMMENDED REFLOW PROFILE



Ramp Up Rate (30-150°C): 1.0-2.0 °C/sec

Pre-heating Time (155-185°C): 30-120 sec

Time Period Above 220°C: 30-100 sec

Ramp Up During Reflow: 1.0-2.0 °C/sec

Peak Temperature: 230-250 °C

Ramp Down Cooling Rate: 1.0-6.0 °C/sec

Note: The recommended reflow profile is provided as a guideline. Optimal profile may differ due to oven type, assembly layout or other process variables.



Lead-Free Solder Paste

PF606-P30

Rev. 2016/03/01 Ver. 02-01

STORAGE & HANDLING:

- Refrigerate the solder paste at 0-10°C. Shelf life is 6 months from production date (sealed package).
- Keep away of direct sunlight.
- Allow the paste to reach defined printing temperature (room temperature) for 3-4 hrs. Do not heat up the solder paste rapidly.
- For jars packaging, mix the solder paste before use for 1-3 mins by plastic spatula.
- It is recommended to finish fresh paste within 24 hrs. Do not store used paste and fresh paste in the same jar.
- If printing process was interrupted for more than 1 hour, remove the remained paste from stencil and seal in the jar.
- Recommended printing environment is 22-28°C and RH 30-60%.

Note: For more information, please refer to solder paste application guideline sheet

HOW TO ORDER

PF606 – P30 – T3 – 500

Solder Alloy	Flux	Particle Size	Weight / Packaging
PF606 = SnAg3.0Cu0.5	P30 = ROLO	T3 = 20-45µm	30 = syringe 30g
		T4 = 20-38µm	100 = syringe 100g
		T5 = 15-25µm	150 = syringe 150g
		T6 = 5-15µm	250 = plastic jar 250g
			500 = plastic jar 500g
			600 = small cartridge 600g
			1200 = large cartridge 1200g



CONTACTS

Tel.: +49-152-5106-5427


support@nevo-solder.com

www.nevo-solder.com

NOTICE: Specifications are subject to change without notice. Contact NeVo® for the latest specifications. All statements, information and data given herein are believed to be accurate and reliable, but are presented without guarantee, warranty, or responsibility of any kind, expressed or implied. Statements or suggestions concerning possible use of our product are made without responsibility or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated or that other measures are indicated or that measures may not be required. Specifications are typical and may not apply to all applications.

NeVo®, Škrobárenská 506/2, 617 00 BRNO, CZECH REPUBLIC